

**PHYSICAL PROPERTIES & PACKAGING (FLOATING MULTILAYER MODULAR FLOORING - 0.197" GAUGE / 8MIL WEAR LAYER)**

Construction Extruded Core Pre-Attached Underlayment	4.0mm (0.157") Solid Polymer Core (SPC) 1.0mm (0.039") HDPE
Use	Light Commercial & Residential ( <b>Refer to Recommended Use PDF for Recommended Areas</b> )
Size	7.08" x 47.64" (180mm x 1210mm)
Wear Layer	8mil (0.2mm)
Edge Detail	Square Edge or Accent Bevel (Inquire with Retailer for Details)
Finish	FX <sup>2</sup> Surface Protectant
Emboss	Barnside
Gauge	5.0mm (0.197")
Pieces/Carton	10
Coverage/Piece	2.344 Sq.Ft. (0.218 Sq.M.)
Coverage/Carton	23.44 Sq.Ft. (2.18 Sq.M.)
Coverage/Pallet	48 Cartons / Pallet (1,125.12 Sq.Ft. / 104.54 Sq.M.)
Coverage/Container	20 Pallets / Container (22,502.4 Sq.Ft. / 2,090.88 Sq.M.)
Limited Warranty	5-Year Light Commercial / 15-Year Residential

**STANDARDS – SAFETY & PERFORMANCE**

Standard	Description	Requirements	Results
ASTM E648	Critical Radiant Flux (Radiant Panel)	Class I: $\geq 0.45 \text{ W/cm}^2$	Passes Requirements <sup>1</sup>
ASTM E662	Smoke Density	Flaming & Non-Flaming $\leq 450$	Passes Requirements <sup>2</sup>
CDPH/EHLB Standard Method v1.2	VOCs/TVOCs, Formaldehyde	Refer to Standard	Passes Requirements
REACH SVHC 181	Substances of Very High Concern	Per Substance: $\leq 0.1\% \text{ w/w}$ (weight/weight)	Passes Requirements
ASTM F963	Heavy Metals	Refer to Standard	Passes Requirements
ASTM D7823 / CPSC-CH-C1001-09.3	Phthalates	Refer to CPSIA <sup>3</sup>	Passes Requirements
ASTM D2047	Coefficient of Friction / Slip Resistance	N/A (No Official Requirements)	$\geq 0.6$ (Dry)
ANSI ESD STM97.2	Body Voltage	N/A (No Official Requirements)	Average (Abs): $\leq 2.0\text{kV}$

**STANDARDS – SOUND**

Standard	Description	Assembly	IBC Requirements <sup>4</sup>	Results
ASTM E90 & ASTM E413	Airborne Sound Transmission Loss of Building Partitions and Elements (STC / Sound Transmission Class)	6" Concrete Slab	STC $\geq 50$	STC 50 (Passes Requirements)
		6" Concrete Slab + Drop-Ceiling	STC $\geq 50$	STC 61 (Surpasses Requirements)
ASTM E492 & ASTM E989	Impact Sound Transmission Through Floor-Ceiling Assemblies (IIC / Impact Insulation Class)	6" Concrete Slab	IIC $\geq 50$	IIC 52 (Surpasses Requirements)
		6" Concrete Slab + Drop-Ceiling	IIC $\geq 50$	IIC 67 (Surpasses Requirements)
ASTM E2179 & ASTM E989	Effectiveness of Floor Coverings in Reducing Impact Sound Transmission ( $\Delta$ IIC / $\Delta$ Impact Insulation Class)	6" Concrete Slab	N/A	$\Delta$ IIC 23

STANDARDS – MANUFACTURING & USAGE (ASTM F3261)			
Standard	Description	Requirements	Results
ISO 24337	Size	Tolerance - Width of 7.08" (180mm) ±0.016" (0.40mm)  Tolerance - Length of 47.64" (1210mm) ±0.060" (1.5mm)	Passes Requirements
ASTM F2421	Squareness	≤0.010" (0.25mm)	Passes Requirements
ASTM F387	Thickness	With Foam Back Layer Tolerance: ±0.008" (0.2mm) vs. Specified Minimum: 0.080" (2.0mm)	Passes Requirements
ISO 24337	Flatness	Max. Values - Width of 7.08" (180mm) F <sub>w</sub> ±0.008" (0.2mm) F <sub>l concave</sub> ≤ 0.15%; F <sub>l convex</sub> ≤ 0.20%	Passes Requirements
ISO 24337	Openings	Average (O <sub>Avg</sub> ) ≤ 0.004" (0.1mm) Maximum (O <sub>M</sub> ) ≤ 0.008" (0.2mm)	Passes Requirements
ISO 24337	Ledging	Average (H <sub>Avg</sub> ) ≤ 0.004" (0.1mm) Maximum (H <sub>M</sub> ) ≤ 0.006" (0.15mm)	Passes Requirements
ASTM F1914	Residual Indentation	Average: ≤0.007" (0.18mm)	Surpasses Requirements
ASTM F1914	Surface Integrity	No puncture through wear layer / décor into rigid core	Passes Requirements
ISO 23999	Dimensional Stability	≤0.25% / lineal ft. (305 mm)	Surpasses Requirements
ISO 23999	Curling	≤0.080" (2.0mm)	Surpasses Requirements
ASTM F925	Chemical Resistance	No more than "Slight Change"	Surpasses Requirements
ASTM F1514	Resistance to Heat	Average ΔE < 8.0	Surpasses Requirements
ASTM F1515	Resistance to Light	Average ΔE < 8.0	Surpasses Requirements
ASTM F970	Static Load	No Official Requirements (Wear Layer < 20mil)	≤0.005" (0.13mm), 250psi
SIM Test	Static Load Limit	Test to Limit (±0.005")	≥1,000psi

**Footnotes**  
 1) ASTM E648 - Critical Radiant Flux (Radiant Panel): Passes Requirements for Class I per International Building Code (IBC) 2018 & NFPA 101 Life Safety Code  
 2) ASTM E662 - Smoke Density: 450 is the limit established by many state, county, and/or local building and/or fire codes, but is not set as a limit for (resilient) flooring products nationwide. Thus, Smoke Density requirements for flooring products may vary from jurisdiction to jurisdiction. Consult your building inspector / fire marshal to learn more.  
 3) CPSIA = Consumer Product Safety Improvement Act  
 4) IBC = International Building Code